


Surmet's AlN Features

- Good sinterability and thermal conductivity
- Very low oxygen and carbon contents
- Low iron and other metallic impurities
- Available in both uncoated and water-resistant grades
- Available in tonnage quantities
- Competitive price
- Manufactured in the U.S



Commercial Grades

A100: Lowest amount of impurities, finest particle size distribution. Typically used for applications requiring high purity, good thermal conductivity and good sinterability.

WR: Water resistant coating suppresses and prevent AlN particles from hydrolysis (AlN is hygroscopic and reacts readily with water/moisture)

WRS: Greater water resistance, more expensive.

Note: Surmet also has capability to produce AlN powders with particle sizes and purity other than specified. [Contact us](#) to find out what can Surmet do for you.

Specifications		Grade
		A100
Particle Size (microns)	Mean/D ₅₀	2 to 6
	D ₉₇	<20
Specific Surface Area (m ² /g)		2.3 to 3.5
Impurities *	Fe	<600 ppm
	Si	<500 ppm
Carbon content		<0.15%
Oxygen content		<1.5%
Availability with WR coating		Yes
Availability with WRS coating		No

* Based on ICP Chemical Analysis

Properties

- Chemical:** Good resistance to several corrosive materials. Compatible with most metals, including Al, Cu, Li, U and ferrous and some superalloys. Resistant to many molten salts including carbonates, chlorides and cryolite.
- Thermal:** 8-10 times more thermally conductive than alumina. Conductivity does not significantly deteriorate with temperature. A relatively low thermal expansion coefficient, which lets AlN meet thermo-mechanical requirements for many electronic device components.
- Electrical:** High dielectric strength and low loss tangent makes AlN a high-performance insulator for many semiconductor, power electronics and thermocouple applications.
- Mechanical:** Hard and durable. Can be fabricated into thin sections with good surface finish.

Applications

Thermal management/Heat extraction: High power LED substrate, electronic packages, fillers for thermally conductive epoxies/adhesives, metal bonded micro-channel coolers, power transformers and transistors, laser diodes, etc.

Dielectric and Microwave: RF output windows, loss buttons, collector and support rods, chip resistors, etc.

Semiconductor: Susceptors and heaters for CVD and dry etching, Crucibles and Evaporation boats for semiconductor crystal growth, Thermocouple shields, etc.

Other applications: High temperature refractories (furnace tooling and components), insulators, etc.

Visit our website www.surmet.com for more information.

Contact us:

Email: sales@surmet.com

Phone: +1 (781) 272-3969